

**Technical Data Sheet (TDS)****Polypropylene (PP) HY03B**

Property	Unit	HY03B
Melt Flow Rate (MFR)	g/10 min	>30
Density	g/cm <sup>3</sup>	0.9
Flexural Modulus	MPa	1200
Tensile Strength at Yield	MPa	25
Elongation at Break	%	200
Izod Impact Strength (23°C)	J/m	150
Heat Deflection Temperature	°C	95
Vicat Softening Temperature	°C	155
Haze	%	8
Applications		Automotive, Consumer Goods, Packaging

For your reference only.

