

# SABIC® LDPE HP0823JN

## LOW DENSITY POLYETHYLENE

### DESCRIPTION

HP0823JN is a Low Density Polyethylene grade formulated with slip and antiblock additives. It typically exhibits good melt strength with good draw down ability. Films typically exhibit good toughness and good biaxial shrink properties

### TYPICAL APPLICATIONS

Shrink film, thin industrial film, thin packaging film, bag & pouches. This grade enables high speed converting without sticking.

### TYPICAL PROPERTY VALUES

Revision 20170709

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 190°C and 2.16 kg	0.80	g/10 min	ASTM D1238
<b>Density</b>			
at 23°C	923	kg/m <sup>3</sup>	ASTM D1505
<b>FORMULATION</b>			
Slip agent	☑	-	-
Anti block agent	☑	-	-
<b>MECHANICAL PROPERTIES</b>			
Dart Impact Strength	2	g/μm	ASTM D1709
<b>OPTICAL PROPERTIES</b>			
Haze <sup>(1)</sup>	10	%	ASTM D1003
<b>Gloss</b>			
at 45°	55	-	ASTM D2457
<b>FILM PROPERTIES</b>			
<b>Tensile Properties</b>			
stress at break, MD	29	MPa	ASTM D882
stress at break, TD	25	MPa	ASTM D882
strain at break, MD	240	%	ASTM D882
strain at break, TD	650	%	ASTM D882
stress at yield, MD	12	MPa	ASTM D882
stress at yield, TD	12	MPa	ASTM D882
1% secant modulus, MD	208	MPa	ASTM D882
1% secant modulus, TD	210	MPa	ASTM D882

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>Tear Resistance</b>			
MD	10	g/μm	ASTM D1922
TD	6	g/μm	ASTM D1922
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>	95	°C	ASTM D1525

(1) Properties have been measured by producing 50 μm film with 2.5 BUR using 100% HP0823N.

## PROCESSING CONDITIONS

Typical processing conditions for HP0823JN are:

Barrel temperature: 170 - 185°C, Blow up ratio: 2.0 – 4.0

## HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, Additional specific information can be requested via your local Sales Office.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical/medical applications.

## STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.